



Technical Data Sheet



Guaranteed Values

Liquid Packaging Board (LPB)

Brand:

KomiBase Aseptic

Parameters	Unit of measure	Test method	Substance (g/m ²)						
			200	220	240	260	280	295	325
Substance tolerance	g/m ²	ISO 536	200±10	220±10	240±10	260±10	280±10	295±10	325±10
Caliper	µm	ISO 534	260±15	310±15	340±15	360±20	390±20	400±20	465±25
Moisture tolerance, min/max	%	ISO 287	7,0±1,0						
Scott plybond, min	J/m ²	TAPPI 569	180						
Bendtsen roughness (top side), max	ml/min	ISO 8791-2	400		600				900
Edge wicking index Lactic Acid (23°C), max	kg/m ²	internal	0,60						
Edge wicking Hydrogen Peroxide (23°C), max	kg/m ²	internal	1,20						

Information:

Mill's certificates

- ISO 9001
- ISO 14001
- ISO 45001

Test conditions: Guaranteed values after conditioning, measured at 50 ± 2% RH and 23 ± 1°C (ISO 187:1990)

System for verifying legal origin of the wood for this product complies with international standard **ISO 38200:2018** Chain of custody of wood and wood based products and Forest Certification Legal Origin standard

Product description:

KomiBase Aseptic is uncoated, hard sized, liquid packaging board (LPB). A double layer baseboard with bleached pulp top layer and kraft (unbleached pulp) bottom layer. For the production of aseptic packaging for liquid products (dairy products, juice, wine)

Valid until: 31.12.2024 or until further notice